



Nikkabright FEN V-A

Absorbance Nikkabright FEN V-A 吸収スペクトル(DMF溶液中・50ppm)



波長	$\lambda_{\max}(362.8 \text{ nm})$
吸光度	0.496

Intensity C.I.FB 135 蛍光スペクトル(DMF溶液中・0.8ppm)



波長	$\lambda_{\text{em}}(428.0 \text{ nm})$	$\lambda_{\text{em}}(410.0 \text{ nm})$	$\lambda_{\text{em}}(460.0 \text{ nm})$
強度	115.0	76.1	77.2

$\lambda_{\text{ex}}=362.8 \text{ nm}$

350～400 nm(紫外線)に励起領域を持ち、410～460 nm(青色光)に蛍光反射領域を持つ。